

Technical Data Sheet

Product Range	Product Name	Dimensional Illustration	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units Per m ²	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) (MPa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	eFactor (mm/m)	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Commons	Dry Press 76		NSW	230	110	76	DW1	3.8	Solid	48.5	384	>15	<15	1.0-8.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Medium
Commons	Exposure 76		NSW	230	110	76	DW1	3	<30	48.5	400	>20	<12	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Medium
Commons	Maxi 119		NSW	290	90	119	DW1	4.4	<30	25.8	276	>15	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Maxi 162		NSW	290	90	162	DW1	6	<30	19.4	208	>15	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Maxi 76		NSW	290	90	76	DW1	2.8	<30	48.5	416	>15	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Standard 119		NSW	230	110	119	DW1	4.5	<30	32.3	265	>25	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Standard 162		NSW	230	110	162	DW1	6	<30	24.25	200	>20	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Standard 76		NSW	230	110	76	DW1	3	<30	48.5	400	>20	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Through Wall 119		NSW	230	150	119	DW1	6.3	<30	32.3	185	>15	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Through Wall 76		NSW	230	150	76	DW1	4	<30	48.5	280	>15	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Universal 76		NSW	230	110	76	DW1	3.2	<30	48.5	400	>25	<12	0.1-4.0	<1.2	General Purpose	Nil to slight	Nil to slight	Medium
Commons	Universal Exposure 76		NSW	230	110	76	DW1	3	<30	48.5	400	>20	<12	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Medium

This data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots. AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.